

Extrulen® 1020 Registered trademark of MediTECH **Ram Extruded Rod Form Data Sheet**

MED-403-A2

Extrulen 1020

Revision 4

29-Sep-11



Raw Material:Ticona GUR 1020
 ISO Cell Designation: Thermoplast ISO 11542-PE-UHMW QD, 2-2-2
 ASTM Cell Designation: S-UHMW-PE0111A111

*Medical Grade PE-UHMW for surgical implants according to ISO 5834-1-e2007, Type 1; ISO 5834-2-2006, Type 1; and ASTM F 648-10a, Type 1

Characteristics of Base Resin: (Source, Ticona®)	Unit	ISO Standard	Required	Avg Typ Values	ASTM Standard	Required	Avg Typ Values
Titanium, trace element; maximum	[mg/kg]	5834-1	40	11	F 648	40	11
Aluminum, trace element; maximum	[mg/kg]	5834-1	20	3.5	F 648	20	3.5
Calcium, trace element; maximum	[mg/kg]	5834-1	5	3	F 648	5	3
Chlorine, trace element; maximum	[mg/kg]	5834-1	30	10	F 648	30	10
Extraneous Particles; maximum	[-]	5834-1	3	0-1	F 648	3	0-1
Glass Transition Temperature Tg	[°C]	3146	na	-110	ISO 3146	na	-110
Crystallization Temperature Range Tc (20-160°C)	[°C]	3146	na	134.5 - 142.5	ISO 3146	na	134.5 - 142.5
Oxidation Induction Time To, conducted @ 200°C	seconds	ASTM D 3895	na	55.32	D 3895	na	55.32
Ash particles, Maximum	[mg/kg]	ISO 3451-1	125	45	ISO 3451-1	125	45
Average Particle Size (Typical)	[mm]	D50	≤16 Sieve	150	D50	≤16 Sieve	150
Average molecular wt [molar mass] according to: Data supplied by Ticona, converted from [IV]	[g/mol*10 ⁶] [g/mol*10 ⁶]	11534-1 Margolies'	na	5.166 - 5.415 4.454 - 4.661	D 4020	na	3.121 - 3.254
Elongational stress Flow Value; F(150/10) minimum	[MPa]	5834-1	≥0.2	0.23	D-4020	≥0.2	0.23
Viscosity Number [RSV]	[mL/g]	5834-1	2000-3200	2197 - 2276	D-4020	2000-3200	2197 - 2276
Porosity; (Bulk Density)	g/cm ³	DIN 53 479	na	.43 - .44	D 1895	na	.43 - .44
Crystallinity; DSC, (1st heat, 20C - 160C)	[%]	3146	na	66.89 - 70.23	D 3417	na	66.89 - 70.23

Conformances: Resin & Fabricated Forms; (Ticona Data)

Optional Processing Available:

***Sterilization (Industry Standard)**

USP Class VI Biocompatibility	Yes	-Ram Extruded Shapes	Ethylene Oxide	Yes
ISO 10993 Cytotoxicity	Yes	-Additive Blended / Compounded	Gas Plasma	Yes
Drug Master File -DMF, EU	10916	-Gamma Cross-Linking	Gamma [inert]	Yes
Drug Master File -DMF, USA	10904	-Inert Atmosphere Processing	Superheated steam 121	No
Device Master File - MAF	588	-Pre-forming and Cut Blocks	Superheated steam 134	No
ISO 5834-1-2005 and 5843-2-2006	Type 1	-High Temperature Thermal Cross-Linking		
ASTM F 648-07e1	Type 1			

*Not conducted by MediTECH

Characteristics of This Annealed, Fabricated Form	Unit	ISO Standard	Required	Avg Typ Values	ASTM Standard	Required	Avg Typ Values
Density, (Annealed Material)	[kg/m ³]	1183	927-944	936 / 1	D792/D1505	927-944	936 / 1
Tensile stress at yield [tensile strength]	[MPa]	527	≥21	23 / 0.3	D 638	≥21	22.6 / 0.4
Tensile stress at break [ultimate tensile strength]	[MPa]	527	≥40	52.9 / 2.5	D 638	≥40	53.1 / 4.4
Elongation Percent at break	[%]	527	≥380	447 / 13	D 638	≥380	502 / 24
Tensile (Young's) modulus; 2mm thick specimens: ASTM Type IV @ 2 mm and ISO Type 5 @ 2 mm	[MPa]	527	na	680 / 40	D 638	na	519 / 31
Notched Impact Strength at 23°C (Charpy, Izod)	[kJ/m ²]	11542-2	180	183.6 / 4.6	F 648	126	149 / 3.5
Shore hardness D-scale, 15 s value	[-]	868	≥60	67 / 1	D 2240	≥60	67 / 1
Poisson's Ratio (*Data supplied by Ticona)	[-]	5834-2	*0.46	*0.46	F 648	*0.46	*0.46
Crystallinity; DSC, (1st heat, 20C - 160C)	[%]	3146	na	>56	D 3417	na	>56
Water absorption at 23 °C until saturation	[%]	62	<0.1	<0.05	D 570	<0.1	<0.05

Thermal Properties (Fabricated Form)

Melting Point DSC, 10K/min	[°C]	3146	na	137.2 / 0.2	D 3417	na	137.2 / 0.2
Vicat softening point, 10N, 50 C°/Hr	[°C]	306	na	134	D 1525 B	na	134
Coef. of Linear thermal expansion; 23 °C to 80 °C	K ⁻¹	11359	na	1.8*10 ⁻⁴	D 696	na	1.8*10 ⁻⁴
Heat Deflection T: HDT/A [1.8 MPa] 66psi/264psi	[°C]	75 pt 1/2	na	[42]	D 648	na	[42]
Thermal Conductivity	[W/(m*K)]	DIN 52612	na	approx. 0.4	DIN 52612	na	approx. 0.4
Glass Transition Temperature Tg	[°C]	DSC	na	-110	DSC	na	-110
Crystallization Temperature Range Tc (20-160°C)	[°C]	DSC	na	126.21 - 143.54	DSC	na	126.21 - 143.54
Oxidation Induction Time To, conducted @ 200°C	seconds	ASTM D 3895	na	18.72	D 3895	na	18.72
Ash particles, maximum	[mg/kg]	ISO 3451 -1	150	60 - 90	ISO 3451-1	150	60 - 90

Ageing Performance Test Results: (ASTM F2101-01); Shelf aged 1 Year in Air Results: Surface Oxidation Index 0.00; Bulk Oxidation Index 0.00

Notice to users: The information on this sheet can not be construed as a promise or guarantee of specific product properties or performance. Any determination of the suitability of a particular material and part design for any use contemplated by the user is the sole responsibility of the user. The information contained in this technical data sheet is based on present knowledge, and may be subject to change without notice.

THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR APPLICATION.

MediTECH shall not be liable and the customer assumes all risk and liability for any use or handling of any material beyond MediTECH's direct control. Full-scale testing and end product performance are the responsibility of the user. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

IMPORTANT: Most plastics will ignite and sustain flame under certain conditions. Caution is urged where any material may be exposed to open flame or heat-generating equipment. Use Material Safety Data Sheets to determine auto-ignition and flashpoint temperatures of materials, or consult MediTECH if additional information is needed.

MediTECH®, Quadrant Website & Location Addresses

For a complete list; locations, contacts, capabilities:

Log onto www.meditechpolymers.com

MediTECH® - Quadrant USA; Fort Wayne, Indiana

MediTECH® - Quadrant Deutschland GmbH; Vreden

MediTECH® - Quadrant United Kingdom; Lancashire

MediTECH® - Quadrant France; Balan

MediTECH® - Quadrant Japan; Tokyo

MediTECH® - Quadrant China; Shanghai