

Chirulen[®] 1020 XPE 75kGy Re-Melted[®] - Registered trademark of MediTECH Compression Molded Form



Data Sheet MED-403-A8.0
Chirulen 1020 X PE 75kGy
Rev 0 21JAN2014 2 pages



Raw Material: Ticona GUR 1020

ISO Cell Designation: Thermoplast ISO 11542-PE-UHMW QD, 2-2-2

ASTM Cell Designation: S-UHMW-PE0111A111

*Medical Grade PE-UHMW for surgical implants according to:
ISO 5834-1-e2007, Type 1; ISO 5834-2-2006, Type 1; and ASTM F 648-13, Type 1

Characteristics of Base Resin: (Summarized from Ticona® C.O.C.'s)	Unit	ISO Standard	Pass Std	Avg Typ Values	ASTM Standard	Pass Std	Avg Typ Values
Titanium, trace element; maximum	[mg/kg]	5834-1	<40	11	F 648	<40	11
Aluminum, trace element; maximum	[mg/kg]	5834-1	<20	3.5	F 648	<20	3.5
Calcium, trace element; maximum	[mg/kg]	5834-1	<5	3	F 648	<5	3
Chlorine, trace element; maximum	[mg/kg]	5834-1	<30	10	F 648	<30	10
Extraneous Particles; maximum	[-]	5834-1	<3	0-1	F 648	<3	0-1
Glass Transition Temperature Tg	[°C]	3146	na	-110	ISO 3146	na	-110
Crystallization Temp Range Tc (20-160°C)	[°C]	3146	na	134.5 - 142.5	ISO 3146	na	134.5 - 142.5
Oxidation Induction Time To, @ 200 °C	seconds	ASTM D3895	na	55.32	D 3895	na	55.32
Ash particles, Maximum	[mg/kg]	ISO 3451-1	125	45	ISO 3451-1	125	45
Average Particle Size (Typical)	[mm]	D50	≤16 Sieve	150	D50	≤16 Sieve	150
Avg. molecular wt [molar mass] according to: Data supplied by Ticona, converted from [IV]	[g/mol*10 ⁶]	11534-1	na	5.166 - 5.415	D 4020	na	3.121 - 3.254
	[g/mol*10 ⁶]	Margolies'	na	4.454 - 4.661			
Elongational stress Flow Value; F(150/10)	[MPa]	5834-1	≥0.2	0.23	D-4020	≥0.2	0.23
Viscosity Number [RSV]	[mL/g]	5834-1	2000-3200	2197 - 2276	D-4020	2000-3200	2197 - 2276
Porosity; (Bulk Density)	g/cm ³	DIN 53 479	na	.43 - .44	D 1895	na	.43 - .44
Crystallinity; DSC, (1st heat, 20C - 160C)	[%]	3146	na	66.89 - 70.23	D 3417	na	66.89 - 70.23

Conformances: Resin & Fabricated Forms; (Ticona Data)

Conformance		Records or Guidance
USP Class VI Biocompatibility & ISO 10993 Cytotoxicity	Yes	Ticona Drug Master File -DMF 10904; USA Ticona Drug Master File -DMF 10916; EU Ticona Device Master File - MAF 588
ASTM F 648-13	Type 1	Powder and Fabricated Forms
ISO 5834-1, 2005	Type 1	Powder Form
ISO 5834-2, Fourth Edition, 01August 2011	Type 1	Fabricated Forms

Optional Processing Technology Available with MediTECH

*Industry Sterilization Methods

Ram Extrusion of rounds and profiles	Ethylene Oxide [ETO]	Yes
Near-Net / Net Shape Molding	Gas Plasma	Yes
Additive / Antioxidant Blending	Gamma [Inert Atmosphere]	Yes
Gamma, E-Beam, X-Ray or Chemical Cross-Linking	Superheated Steam 121 °C	No
Inert Atmosphere Processing	Superheated Steam 134 °C	No
Specialized Fabrication: Pre-Forms, Fixturable Pucks	*These are not conducted by MediTECH	

MediTECH®, Quadrant Website & Location Addresses

MediTECH® - Quadrant USA; Fort Wayne, Indiana	MediTECH® - Quadrant France; Balan
MediTECH® - Quadrant Deutschland GmbH; Vreden	MediTECH® - Quadrant Japan; Tokyo
MediTECH® - Quadrant United Kingdom; Lancashire	MediTECH® - Quadrant China; Shanghai

For a complete list; locations, contacts, capabilities: Log onto www.meditechpolymers.com

Chirulen® 1020 XPE 75kGy Re-Melted Registered trademark of MediTECH Compression Molded Form



Data Sheet MED-403-A8.0
Chirulen 1020 X PE 75kGy
Rev 0 21JAN2014 2 pages



Characteristics of This Annealed, Cross-linked, Fabricated Form	Unit	ISO Standard	Pass Std	Avg Typ Values	ASTM Standard	Pass Std	Avg Typ Values
Density, (Annealed Material)	[kg/m ³]	1183	927 - 944	931/0.1	D792/D1505	927-944	932/0.6
Tensile stress at yield [tensile strength]	[MPa]	527	≥21	19.8/0.3	D 638	20/0.3	21/0.2
Tensile stress at break [ultimate tensile strength]	[MPa]	527	≥35	47.3/1.7	D 638	≥40	48.8/1.6
Elongation Percent at break	[%]	527	≥300	338/11	D 638	≥380	352/9
Tensile (Young's) modulus; 2mm thick specimens:	[MPa]	527	na	660 / 37	D 638	na	500 / 32
Tensile Properties Conducted following: [ASTM Type IV @ 50 mm per minute and ISO Type 1B @ 100 mm per minute]							
Notched Impact Strength at 23 °C (Charpy, Izod)	[kJ/m ²]	11542-2	180	79/1	F 648	126	72/1
Shore hardness D-scale, 15 s value	[-]	868	≥60	65.4/0.5	D 2240	≥60	65.4/0.5
Poisson's Ratio (*Data supplied by Ticona)	[-]	5834-2	*0.46	*0.46	F 648	*0.46	*0.46
Crystallinity; DSC, (1st heat, 20C - 160C)	[%]	3146	na	53/0.8	F2625	na	53/0.8
Water absorption at 23 °C until saturation	[%]	62	<0.1	<0.05	D 570	<0.1	<0.05
Thermal Properties (Fabricated Form)							
Melting Point DSC, 10K/min	[°C]	3146	na	136.5 / 0.5	F2625	na	136.5 / 0.5
Vicat softening point, 10N, 50 °C/Hr	[°C]	306	na	134	D 1525 B	na	134
Coef. of Linear thermal expansion; 23 °C to 80 °C	K ⁻¹	11359	na	1.8*10 ⁻⁴	D 696	na	1.8*10 ⁻⁴
Heat Deflection T: HDT/A [1.8 MPa] 66psi/264psi	[°C]	75 pt 1/2	na	[42]	D 648	na	[42]
Thermal Conductivity	[W/(m*K)]	DIN 52612	na	approx. 0.4	DIN 52612	na	approx. 0.4
Glass Transition Temperature Tg	[°C]	DSC	na	-110	DSC	na	-110
Crystallization Temperature Range Tc (20-160°C)	[°C]	DSC	na	126.21 - 143.54	DSC	na	126.21 - 143.54
Oxidation Induction Time To, conducted @ 200 °C	Minutes	D 3895	na	18.72	D 3895	na	Results Available April 2014
Ash particles, maximum	[mg/kg]	ISO 3451 -1	150	60 - 90	ISO 3451-1	150	60 - 90

**Oxidation Resistance Test Results: (ASTM F2101-01 AND ISO 5834-4; 2005);
Shelf aged 1 Year in Air Results: Surface Oxidation Index **0.0**; Bulk Oxidation Index **0.0****

Regulatory Submission Support Available through MediTECH for Enhanced Forms

Produce Materials to customer specifications; Characterize and report according to validation protocols as evidence for new product development and submission according to:

ASTM F 2565-13; "Standard Guide for Extensively Irradiation-Crosslinked Ultra-High Molecular Weight Polyethylene Fabricated Forms for Surgical Implant Applications^{1"}

ASTM F 2695-12; "Standard Specification for Ultra-High Molecular Weight Polyethylene Powder Blended with Alpha-Tocopherol (Vitamin E) and Fabricated Forms for Surgical Implant Applications^{1"}

ASTM F 2759; "Standard Guide for Assessment of the Ultra High Molecular Weight Polyethylene (UHMWPE) Used in Orthopedic and Spinal Devices^{1"}

Notice to users: The information on this sheet can not be construed as a promise or guarantee of specific product properties or performance. Any determination of the suitability of a particular material and part design for any use contemplated by the user is the sole responsibility of the user. The information contained in this technical data sheet is based on present knowledge, and may be subject to change without notice.

THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR APPLICATION.

MediTECH shall not be liable and the customer assumes all risk and liability for any use or handling of any material beyond MediTECH's direct control. Full-scale testing and end product performance are the responsibility of the user. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

IMPORTANT: Most plastics will ignite and sustain flame under certain conditions. Caution is urged where any material may be exposed to open flame or heat-generating equipment. Use Material Safety Data Sheets to determine auto-ignition and flashpoint temperatures of materials, or consult MediTECH if additional information is needed.